

### General Description and Use

Argotec SKU Number	<b>18215</b>	
Typical application	Die cut and seal	
Polymer	Thermoplastic polyurethane; aromatic polyether	
Extrusion method	Blown film	
Gauge	1.0 - 10 mils (25 - 250 microns)	
Width	Up to 86 inches (2.18 meters)	
Length	Up to 1000 non-spliced yards (914.4 meters)	
Key attributes	<ul style="list-style-type: none"> <li>■ Smooth surface</li> <li>■ Soft ether</li> <li>■ Mid-range softening temperature</li> </ul>	
Typical Properties	Test Method	Value
Durometer	ASTM D-2240	Shore 87A
Tensile stress @ 100% elongation	ASTM D-412	1000 psi 6.89 MPa
Tensile stress @ 300% elongation		1700 psi 11.72 MPa
Tensile strength		5500 psi 37.92 MPa
Elongation at break		600%
Tensile set at 200% E		15%
Tear strength	D-624 <sup>1</sup>	435 pli 76.13 kN/m
Abrasion resistance	D-1044 <sup>2</sup>	5 mg loss

<sup>1</sup> Die C.

<sup>2</sup> Taber abrasion CS-17 wheel, 1000 gm weight, 1000 cycles.

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.