

General Description and Use

Argotec SKU Number	18305	
Typical application	Industrial; textile lamination; antistatic	
Polymer	Thermoplastic polyurethane, aromatic polyether	
Extrusion method	Blown film	
Gauge	1.0 - 10 mils (25 - 250 microns)	
Width	Up to 86 inches (2.18 meters)	
Length	Up to 1000 non-spliced yards (914.4 meters)	
Key attributes	<ul style="list-style-type: none"> ■ Smooth surface ■ Soft ether ■ Mid-range softening temperature ■ Antistatic additive 	
Typical Properties	Test Method	Value
Durometer	ASTM D-2240	Shore 84A
Tensile stress @ 100% elongation	ASTM D-412	900 psi 6.2 MPa
Tensile stress @ 300% elongation		2300 psi 15.9 MPa
Tensile strength		7300 psi 50.4 MPa
Elongation at break		500%
Tensile set at 200% E		18%
Tear strength	D-624 ¹	480 pli 84.1 kN/m

¹ Die C.

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.