

General Description and Use

Argotec SKU Number	19426
Typical application	Textile lamination
Polymer	Thermoplastic polyurethane, aromatic polyether
Extrusion method	Blown film
Gauge	1.0 - 10 mils (25 - 250 microns)
Width	Up to 86 inches (2.18 meters)
Length	Up to 1000 non-spliced yards (914.4 meters)
Key attributes	<ul style="list-style-type: none"> ■ Smooth surface ■ Hardest ether ■ Highest softening temperature ■ No inorganic wax

Typical Properties	Test Method	Value
Durometer	ASTM D-2240	Shore 95A
Tensile stress @ 100% elongation	ASTM D-412	1750 psi 12 MPa
Tensile stress @ 300% elongation		3000 psi 21 MPa
Tensile strength		5200 psi 36 MPa
Elongation at break		490%
Tensile set at break		65%
Tear strength	D-624 ¹	800 pli 140 kN/m
Abrasion resistance	D-1044 ²	55 mg loss
Typical melt temperature		198 - 208°C 388 - 406°F

¹ Die C.

² Taber abrasion CS-17 wheel, 1000 gm weight, 1000 cycles.

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.