

General Description and Use

Argotec SKU Number	28304	
Typical application	Textile lamination	
Polymer	Thermoplastic polyurethane, aromatic polyester	
Extrusion method	Blown film	
Gauge	1.0 - 10 mils (25 - 250 microns)	
Width	Up to 86 inches (2.18 meters)	
Length	Up to 1000 non-spliced yards (914.4 meters)	
Key attributes	<ul style="list-style-type: none"> ■ Smooth surface ■ Soft ester ■ Mid-range softening temperature 	
Typical Properties	Test Method	Value
Durometer	ASTM D-2240	Shore 85A
Tensile stress @ 100% elongation	ASTM D-412	800 psi 6 MPa
Tensile stress @ 300% elongation		1400 psi 10 MPa
Tensile strength		6000 psi 41 MPa
Elongation at break		600%
Tear strength	D-624 ¹	500 pli 88 kN/m

¹ Die C.

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.