

General Description and Use

Argotec SKU Number	D7101
Typical application	Die cut and seal
Polymer	Thermoplastic polyurethane, aromatic polyether
Extrusion method	Flat die
Gauge	10 - 125 mils (250 - 3125 microns)
Width	Up to 60 inches (1.52 meters)
Length	Up to 1000 non-spliced yards (914.4 meters)
Key attributes	<ul style="list-style-type: none"> ■ Clear surface ■ Rigid ether

Typical Properties	Test Method	Value
Durometer	ASTM D-2240	Shore 72D
Specific gravity	ASTM D-792	1.20
Tensile strength	ASTM D-638	10,000 psi 69 MPa
Elongation at break	ASTM D-412	160%
Flexural modulus	ASTM D-790	330,000 psi 2,300 MPa

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.